

# Comment on “Collapse of Coherent Quasiparticle States in $\Theta$ -(BEDT-TTF) $_2$ I $_3$ Observed by Optical Spectroscopy”

Recently, Takenaka *et al.*[1] reported that the resistivity  $\rho(T)$  of  $\Theta$ -(BEDT-TTF) $_2$ I $_3$  ( $\Theta$ -ET) exceeds the Ioffe-Regel resistivity,  $\rho_{IR}$ , by a factor of 50 at large temperatures  $T$  (“bad metal”). This was ascribed to strong correlation. We show that the optical conductivity  $\sigma(\omega)$  implies that correlation is not very strong for  $\Theta$ -ET, and that correlation gives no general strong suppression of  $\sigma(\omega)$ . The large  $\rho(T)$  is primarily due to a downturn in  $\sigma(\omega)$  at small  $\omega$ , earlier emphasized by Takenaka *et al.* [2] as the explanation for bad metal behavior of high- $T_c$  cuprates. We show, however, that for cuprates strong correlation is the main effect. The data of Takenaka *et al.*[1] puts  $\Theta$ -ET in a new class of bad metals.

To put  $\Theta$ -ET into context, we discuss a theory of resistivity saturation [3]. We use an f-sum rule, relating the integral over  $\sigma(\omega)$  to the electron hopping energy,  $E_K$ . We assume that  $T$  is so large that the Drude peak is smeared out and that  $\sigma(\omega)$  varies smoothly over the band width  $W$  (shown for Nb $_3$ Sb in Fig. 1). We obtain

$$\sigma(0) = \frac{\gamma}{W} \int_0^\infty \sigma(\omega) d\omega \sim \frac{|E_K|}{W}, \quad (1)$$

where  $\gamma \sim 1 - 2$ . Assuming i) noninteracting electrons and ii)  $T \ll W$ , we estimate  $E_K$ . Inserting  $E_K$  in Eq. (1) gives  $\sigma(0)$  and a quantum-mechanical derivation of the Ioffe-Regel condition,  $l \gtrsim d$ , where  $l$  is the apparent mean free path and  $d$  is a typical atomic separation [3].

Assumption i) is invalid for cuprates, and correlation drastically reduces  $|E_K|$ . Estimating  $E_K$ , we obtained the saturation resistivity  $\rho_{sat}$  for La $_{2-x}$ Sr $_x$ CuO $_4$  (LSCO) [3]. Experimental data do not exceed  $\rho_{sat}$ , and  $\rho(T, x)$  curves approaching  $\rho_{sat}$  appear to saturate. Fig. 1 shows that strong correlation reduces  $\sigma(0)$  of LSCO ( $x=0.06$ ,  $T=295$  K) by a factor of four relative to  $1/\rho_{IR}$ , with room for further reduction to  $1/\rho_{sat}$  with increasing  $T$ .

Assumption ii) is invalid for A $_3$ C $_{60}$  (A=K, Rb). This leads to a violation of the Ioffe-Regel condition due to coupling to intramolecular phonons [3].

For the quarter-filled  $\Theta$ -ET,  $\omega$ -integrated  $\sigma(\omega)$  data for small  $T$  and the f-sum rule suggest that correlation does not strongly reduce  $|E_K|$ , in strong contrast to cuprates. As a result,  $\sigma(\omega)\rho_{IR} \sim 1$ , comparable to Nb $_3$ Sb, except for very small  $\omega$ . As in the cuprates, there is a downturn in  $\sigma(\omega)$  at small  $\omega$ . While this is a small effect in cuprates, reducing  $\sigma(0)$  by about 10-20 % in Fig. 1 (compared with dashed line), the  $\Theta$ -ET data [1] imply a reduction of  $\rho(T = 295)$  by a factor of 50-100. Thus the absence of such a downturn is a third assumption (iii) for deriving the Ioffe-Regel condition, putting  $\Theta$ -ET in a third class of bad metals. The energy scale of the downturn,  $\sim T$ , is very small, raising questions why the struc-




FIG. 1:  $\sigma(\omega)\rho_{IR}$  as a function of  $\omega/W$  for Nb $_3$ Sb (theory) [3], LSCO [2],  $\Theta$ -ET [1] and  $\kappa$ -ET [4], where (the noninteracting)  $W$  is 8, 3.2, 0.7 and 1.0 eV, respectively. The value 1.0 eV is chosen unrealistically large to show all main features. The sharp phonon structures at small  $\omega$  and interband transitions for LSCO for  $\omega/W \gtrsim 0.3$  are not of interest here. The dashed curve indicates a  $\sigma(\omega)$  of LSCO without downturn. The Ioffe-Regel condition implies  $\sigma(0)\rho_{IR} \gtrsim 1$ .

ture is not thermally smeared out. The  $T$  dependence of the integrated  $\sigma(\omega)$  [1] shows similarities with calculations [3] for A $_3$ C $_{60}$  emphasizing intramolecular phonons, raising questions about the role of phonons for  $\Theta$ -ET.

Fig. 1 shows that  $\sigma(\omega)\rho_{IR}$  is suppressed for the “half-filled” (BEDT-TTF) $_2$ Cu[N(CN) $_2$ ]Br $_{0.85}$ Cl $_{0.15}$  ( $\kappa$ -ET) due to correlation reducing  $|E_K|$  and expanding the energy scale. There is also a downturn, although less dramatic and on a larger energy scale than for  $\Theta$ -ET. Thus both assumptions i) and iii) are moderately violated.

The results for, in particular,  $\Theta$ -ET raise interesting questions about the role of quasi-two-dimensional triangular lattices with phonons and Coulomb interaction.

O. Gunnarsson and K. Vafayi  
Max-Planck-Institut für Festkörperforschung,  
D-70506 Stuttgart, Germany

Pacs:72.10.-d, 72.80.Le,72.80.Ga

- 
- [1] K. Takenaka *et al.*, Phys. Rev. Lett. **95**, 227801 (2005).
  - [2] K. Takenaka *et al.*, Phys. Rev. B **65**, 092405 (2002).
  - [3] O. Gunnarsson *et al.*, Rev. Mod. Phys. **75**, 1085 (2003); M. Calandra and O. Gunnarsson, Phys. Rev. B **66**, 205105 (2002).
  - [4] D. Faltermeier *et al.*, cond-mat/0608090.